



LUND UNIVERSITY

Evaporative resistance testing that allows detailed feedback for customers: a case of the Latvian Army

Kuklane, Kalev; Sitvjenkins, Igors

2016

Document Version:

Publisher's PDF, also known as Version of record

[Link to publication](#)

Citation for published version (APA):

Kuklane, K., & Sitvjenkins, I. (2016). *Evaporative resistance testing that allows detailed feedback for customers: a case of the Latvian Army*. 93-94. Abstract from 11th International Meeting on Thermal Manikin and Modeling, Suzhou, China.

Total number of authors:

2

General rights

Unless other specific re-use rights are stated the following general rights apply:

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

Read more about Creative commons licenses: <https://creativecommons.org/licenses/>

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

LUND UNIVERSITY

PO Box 117
221 00 Lund
+46 46-222 00 00

Clothing Evaporative Resistance Testing that Allows Detailed Feedback for Customers: A Case of the Latvian Army

Kalev Kuklane^{1,*}, Igors Sitvjenkins²

¹ Thermal Environment Laboratory, Ergonomics and Aerosol Technology, Lund University, Lund, Sweden

² Joint HQ Logistics (J-4) Department, National Armed Forces of the Republic of Latvia, Riga, Latvia

*Corresponding author: Assoc. Prof. Kalev Kuklane, E-mail: kalev.kuklane@design.lth.se

Abstract

Two most important clothing properties are thermal insulation and evaporative resistance. Clothing insulation is not evenly distributed over the body surface. Body regions' insulation values can be measured, and the change due to walking and wind can be estimated. Today the development of the testing methods allows the same even for evaporative resistance [1, 2]. Local values can be used in advanced physiological models [3]. The major aim of this study was to provide the Latvian Army with regional evaporative resistance values of selected garment ensembles. An aim was to set up the methodology, standardised procedures and forms for regional evaporative resistance measurements, calculations and corrections at the laboratory.

A textile skin and 4 sets of clothing were tested: Set 1 – short sportswear for warm season; Set 2 – long sportswear for cold season; Set 3 – summer combat uniform; Set 4 – dry suit set. Evaporative resistance was calculated by the heat loss method as the regional evaporative resistance values were of interest. Tests were carried out at so-called homogenous test conditions where manikin surface (T_s) and environmental temperatures ($T_a=T_r$) were kept at 34 °C. Textile skin temperature (T_{sk}) was corrected by heat loss (HL): $T_{sk}=T_s-a \times HL$ [2, 4]. Air velocity in the chamber was kept at 0.30 ± 0.09 m/s. Heat loss of the whole manikin and the individual zones was corrected for surface temperature, and heat gain from environment. As skin itself has evaporative resistance then clothing evaporative resistance (R_{ecl}) was calculated by subtracting skin and air layer evaporative resistance from the total evaporative resistance (R_{et}). Clothing area factor (f_{cl}) was acquired according to EU Subzero project final report for this correction. Several factors were not considered: clothing insulation change due to wetness, skin thickness and material effects etc.

Table 1. Insulation and evaporative resistance of the tested clothing ensembles.

Ensemble	I_{tot} m ² ·K/W	R_{et} m ² ·Pa/W	i_m	f_{cl}	R_{ecl} m ² ·Pa/W	$R_{ecl,torso}$ m ² ·Pa/W	$R_{ecl,arms}$ m ² ·Pa/W	$R_{ecl,legs}$ m ² ·Pa/W
Air layer	0.090	-	-	-	-	-	-	-
Skin	0.125	11.3	0.68	1.11	-	-	-	-
Set 1	0.135	16.0	0.58	1.11	4.8	7.2	1.7	4.3
Set 2	0.220	23.2	0.58	1.19	12.6	15.4	9.5	11.7
Set 3	0.222	33.9	0.39	1.19	23.5	40.8	14.0	20.4
Set 4	0.244	109.3	0.18	1.21	103.4	111.2	81.9	85.6

Note: -, not applicable.

The total insulation and evaporative resistance, permeability index and clothing area factor, and total and area specific clothing evaporative resistance values are shown in Table 1. The customer did receive the total and 14 local evaporative resistance values for each selected clothing ensemble. Various corrections in combination with unknown factors may allow wide interpretation of the methodology. There is a need to set basic standard guidelines on the specific evaporative resistance determination process.

References:

[1] Ueno S, Sawada SI (2012) Correction of the evaporative resistance of clothing by the temperature of skin fabric on a sweating and walking thermal manikin. *Text. Res. J.* **82**(11):1143-1156.

- [2] Wang F, del Ferraro S, Lin LY, Mayor TS, Molinaro V, Ribeiro M, Gao C, Kuklane K, Holmér I (2012) Localised boundary air layer and clothing evaporative resistances for individual body segments, *Ergonomics* **55**(7):799-812.
- [3] Fiala D, Havenith G (2015) Modelling Human Heat Transfer and Temperature Regulation. In: Gefen A (ed.) *Studies in Mechanobiology, Tissue Engineering and Biomaterials*. Springer. pp.1-38.
- [4] Wang F, Kuklane K, Gao C, Holmér I (2010) Development and validity of a universal empirical equation to predict skin surface temperature on thermal manikins. *J. Therm. Biol.* **35**(4):197-203.