LUND UNIVERSITY

Effect of Gate Oxide Defects on Tunnel Transistor RF Performance

Hellenbrand, Markus; Memisevic, Elvedin; Svensson, Johannes; Krishnaraja, Abinaya; Lind, Erik; Wernersson, Lars-Erik

Published in:
2018 76th Device Research Conference (DRC)

DOI:
[10.1109/DRC.2018.8442145](https://doi.org/10.1109/DRC.2018.8442145)

2018

Document Version:
Peer reviewed version (aka post-print)

[Link to publication](#)

Citation for published version (APA):
Hellenbrand, M., Memisevic, E., Svensson, J., Krishnaraja, A., Lind, E., & Wernersson, L-E. (2018). Effect of Gate Oxide Defects on Tunnel Transistor RF Performance. In *2018 76th Device Research Conference (DRC)* (pp. 137-138). IEEE - Institute of Electrical and Electronics Engineers Inc..
<https://doi.org/10.1109/DRC.2018.8442145>

Total number of authors:
6

General rights

Unless other specific re-use rights are stated the following general rights apply:
Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

Read more about Creative commons licenses: <https://creativecommons.org/licenses/>

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

LUND UNIVERSITY

PO Box 117
221 00 Lund
+46 46-222 00 00

Effect of Gate Oxide Defects on Tunnel Transistor RF Performance

M. Hellenbrand, E. Memisevic, J. Svensson, A. Krishnaraja, E. Lind, and L.-E. Wernersson

Lund University, Department of Electrical and Information Technology

Ole Römers väg 3, 22363 Lund, Sweden

Email: markus.hellenbrand@eit.lth.se

Overview

Tunnel field-effect transistors (TFETs) are designed for low off-state leakage and low drive voltages. To investigate how capable TFETs are of RF operation, we measured their scattering parameters and performed small-signal modeling. We find that in the low frequency ranges, gate oxide defects have a major influence on the RF performance of these devices, which can be modeled by a frequency-dependent gate-to-drain conductance $g_{gd,\omega}$. This model is based on charge trapping in gate oxide defects and was studied before for metal-oxide-semiconductor capacitors [1].

Devices and Measurement

All TFETs in this work are based on vertical III-V nanowire structures. To achieve sufficiently high RF gain, all measured devices consisted of arrays of up to 2000 nanowires. Arrays this large deteriorate the inverse subthreshold slope S from typical values below 60 mV/decade for devices with only a few nanowires to about 75 to 200 mV/decade (Fig. 1(b)). The maximum intrinsic transconductance for most of the measured RF devices was about 113 $\mu\text{S}/\mu\text{m}$ at $V_{DS} = 0.5$ V. A schematic structure of one nanowire inside an array is depicted in Fig. 1(a) and details about the fabrication can be found in [2] and [3]. The RF measurement setup was calibrated off-chip, all measurements were de-embedded by dedicated open and short structures on the respective sample, and modeling was performed according to the model in Fig. 1(c), which also presents representative values for all small-signal parameters. The difference in the real parts of the y -parameters with and without frequency dependence is evident in Fig. 2(a).

Modeling and Physical Explanation

Electrons can tunnel into and out of gate oxide defects from the channel and from the gate contact, and the tunnel time constant of this process, modeled as the frequency-dependent conductance $g_{gd,\omega}$, causes a phase shift relative to the small-signal voltage excitation. Above a certain frequency, the time constants of all defects is too long for the defects to respond to the small-signal excitation so that the effect decreases at higher frequencies. The phase shift effectively constitutes a loss in the RF power gain U (clearly visible in Fig. 2(c)) and a shift of the real parts of the y -parameters (Fig. 2(a)). This sensitivity to oxide defects can be used as a general material characterization method. In the case of TFETs, a frequency dependence only occurs in g_{gd} , not in g_{gs} , and with the example of $\text{Re}(y_{11}) \approx \omega g_{gd,\omega} + \omega^2 (C_{gs} + C_{gd})^2 R_g$ with the parameters from the model in Fig. 1(c) (without R_s and R_d), the shift from the frequency-dependent part of g_{gd} is evident. Constant contributions to g_{gd} or g_{gs} , representing gate leakage, were found to be negligible besides the frequency-dependent component of g_{gd} .

The asymmetry between source and drain provides insight into the charge distribution and transport mechanism of TFETs, since it indicates that the tunnel junction on the source side decouples the small-signal responses between source and channel. Furthermore, it indicates that the majority of the channel charge is supplied by the drain side, since increasing V_{DS} depletes the drain side of the channel of charge so that the same variation due to gate oxide defects has less impact and $g_{gd,\omega}$ decreases (Fig. 3(a)). The opposite happens when the amount of charge in the channel is increased by increasing the gate bias V_{GS} for a constant V_{DS} . This lowers the barrier from the drain towards the channel, allowing more charge carriers to enter the channel, and $g_{gd,\omega}$ increases with the charge (Fig. 3(b)).

The same asymmetry between source and drain and the same bias dependence were observed for the intrinsic capacitances in TFETs, where the gate-to-source capacitance C_{gs} turned out to be much smaller than the gate-to-drain capacitance C_{gd} [4]. Different from $g_{gd,\omega}$, however, the intrinsic C_{gd} eventually becomes zero at high V_{DS} or low V_{GS} , when the channel is completely depleted of charge. The reason why $g_{gd,\omega}$ does not become zero in the same manner is probably the large parasitic capacitance between the gate metal contact and the n+ InAs drain layer (cp. Fig. 1). Since the gate oxide is not only adjacent to the channel, but also to the gate-drain spacer, there are parasitic losses in these layers as well, which remain present even when the channel is depleted of carriers.

In summary, we have analyzed and explained the effect of gate oxide defects on the RF performance of TFETs.

[1] Y. Yuan et al., IEEE-EDL, vol. 32, p. 485, (2011).

[3] E. Memisevic et al., IEEE-TED, vol. 64, p. 4746, (2017).

[2] E. Memisevic et al., Nano Lett., vol. 17, p. 4373, (2017).

[4] M. Hellenbrand et al., submitted to IEEE-EDL, (Feb. 2018).

This work was supported in part by the Swedish Foundation for Strategic Research and the Swedish Research Council, and in part by the European Union Seventh Framework Program E2SWITCH under Grant 619509.

Fig. 1: (a) Schematics of a single nanowire inside an array. (b) Example transfer curves for an RF array (minimum $S = 75\text{ mV/decade}$) and a device with two nanowires (minimum $S = 53\text{ mV/decade}$). (c) Small-signal model with representative values. Note the frequency dependence of g_{gd} and the absence of g_{gs} .

Fig. 2: Full small-signal model for a TFET, solid lines are the measured values. (a) Real parts of the y-parameters with and without frequency dependence as red, broken and red, dotted lines, respectively. The difference is clearly visible. (b) Imaginary parts not affected by frequency-dependence. (c) The unitary power gain U is greatly affected by the frequency dependence in g_{gd} , but MAG , MSG , and h_{21} remain unchanged.

Fig. 3: Bias dependence of the frequency-dependent parts of the small-signal conductances, normalized to the total gate width. Different curves represent different transistors. (a) $g_{gd,\omega}$ decreases with increasing V_{DS} because the drain side of the channel is depleted and the variations due to gate oxide defects have less impact. (b) $g_{gd,\omega}$ increases with increasing V_{GS} , since charge is accumulated in the channel.